



Kimia Baspar Golpa

PA66MIG210

Nylon66+Glass Fiber

General Information

● **Characteristic:** Injection grade, Medium Impact, High Strength & Rigidity Mechanical Strength

Physical Property

Property	Test method	Test condition	Unit	Nominal Values
Mechanical Property				
Notched Izod impact	ASTM D256	23°C, 3.2mm	KJ/m ²	7
Rock well hardness	ASTM D-785	R-Scal	R-Scal	120
Tensile Strength at yield	ASTM D638	23°C, 50 mm/min	Mpa
Tensile Strength at Break			Mpa	120
Elongation at break			%	4
Flexural modulus	ASTM D790	23°C 10mm/min	Mpa	5000
Flexural strength			Mpa	170
Flammability				
Flammability	UL94	¼ inch (3.2 mm)	HB (<76mm/min)	HB
Thermal Property				
HDT(Heat Deflection Temp)	ASTM D648	unannealed 0.46MPa	°C	240
HDT(Heat Deflection Temp)	ASTM D648	unannealed 1.8MPa	°C	230
Polymer property				
Melting Point	DSC Method	°C	260
Density	ASTMD792	23°C	g/cm ³	1.23
Mold shrinkage	ASTM D955	100*100*3.2 mm	%	0.3~0.8
Water Absorption	ASTM D570	23°C, water, 24h	%	2.0
Electrical				
Dielectric Strength	ASTM D149	Kv/mm	25
Volume Resistivity	ASTM D257	Ω.cm	10 ¹⁵
Dielectric Constant	ASTM D150	10 ⁶ HZ

1-typical values are not our specification and not be used for part or tool design.

2-all properties ,except Melt Flow Index are measured on injection molded specimens and after 48 hour storage at 23°C and in RH of 50%..

www.kbgco.ir

PA66MIG210**Nylon66+Glass Fiber****Processing guid (Injection molding condition)**

Processing parameters	unit	value	
Drying Temperature	°C	90~110	
Drying Time	hrs	2~4	
Moisture content	%	<0.1	
Melt Temperature	°C	260	
Cylinder Temperature	Rear	°C	270~280
	Middle	°C	270~280
	Front	°C	270~280
Nozzle Temperature	°C	280~290	
Mold Temperature	°C	70~90	
Injection Pressure	kg/cm ²	60~150	
Screw Speed	rpm	30~60	

Note): Some modifications may be required depending on the specific molding equipment and part configuration.

www.kbgco.ir