



# Kimia Baspar Golpa

**PA6GPM1020**

**PA6+Mineral Filler**

## General Information

● **Characteristic:** Injection grade, Medium Impact, good strength, chemical and abrasion resistance., Weather Resistance, Dimension Stability, Good surface Effect

## Physical Property

Property	Test method	Test condition	Unit	Nominal Values
<b>Mechanical Property</b>				
Notched Izod impact	ASTM D256	23°C, 3.2mm	KJ/m <sup>2</sup>	6
Rock well hardness	ASTM D-785	R-Scal	R-Scal	120
Tensile Strength at yield	ASTM D638	23°C , 50 mm/min	Mpa	65
Elongation at break			%	10
Flexural modulus	ASTM D790	23°C 10mm/min	Mpa	3500
Flexural strength			Mpa	110
<b>Flammability</b>				
Flammability	UL94	¼ inch (3.2 mm)	HB (<76mm/min)	HB
<b>Thermal Property</b>				
HDT(Heat Deflection Temp)	ASTM D648	unannealed 0.46MPa	°C	120
HDT(Heat Deflection Temp)	ASTM D648	unannealed 1.8MPa	°C	65
<b>Polymer property</b>				
Melting Point	DSC Method	....	°C	220
Density	ASTMD792	23°C	g/cm <sup>3</sup>	1/26
Mold shrinkage	ASTM D955	100*100*3.2 mm	%	1.1~1.5
Water Absorption	ASTM D570	23°C, water, 24h	%	1/4
<b>Electrical</b>				
Dielectric Strength	ASTM D149	....	Kv/mm	22
Volume Resistivity	ASTM D257	....	Ω.cm	10 <sup>13</sup> ~10 <sup>15</sup>
Dielectric Constant	ASTM D150	....	10 <sup>6</sup> HZ	4

typical values are not our specification and not be used for part or tool design.

2-all properties ,except Melt Flow Index are measured on injection molded specimens and after 48 hour storage at 23°C and in RH of 50%..

[www.kbgco.ir](http://www.kbgco.ir)

**PA6GPM1020****PA6+Mineral Filler****Processing guid (Injection molding condition)**

Processing parameters	unit	value	
Drying Temperature	°C	90~110	
Drying Time	hrs	2~4	
Moisture content	%	<0.1	
Melt Temperature	°C	220	
Cylinder Temperature	Reare	°C	210~220
	Middle	°C	220~230
	Front	°C	220~230
Nozzel Temperature	°C	220~230	
Mold Temperature	°C	60~80	
Injection Pressure	kg/cm <sup>2</sup>	60~150	
Screw Speed	rpm	30~60	

**Note):**Some modifications may be required depending on the specific molding equipment and part configuration.

[www.kbgco.ir](http://www.kbgco.ir)