



Kimia Baspar Golpa

PPHR1085

HIPP+ RUBBER+MF

General Information

● **Characteristic:** Hi impact strength, low temperature toughness, Excellent Formability, easy coating, dimensional stability, good process ability, Weather Resistance

● **Application:** Exterior parts Bumper assembly, Bumper Fascia

Physical Property

Property	Test method	Test condition	Unit	Nominal Values
Mechanical Property				
Notched Izod impact	ASTM D256	23°C	KJ/m2	52
		-20 °c	KJ/m2	13
Hardness	ASTM D2240-05	23°C, 15sec	Shore D	58
**Scratch Resistance	ISO7724Method A	10N	ΔL
Tensile stress at yield	ASTM D638	23°C , 50 mm/min	Mpa	17.5
Tensile strength at break			Mpa	15
Tensile modulus			Mpa	750
Elongation at Yield			%	7
Elongation at break			%	320
Flexural modulus			ASTM D790	23°C
Flexural strength	Mpa	27		
Flammability				
Flammability	UL94	½ inch (3.2 mm)	HB (<76mm/min)	HB
Thermal Property				
HDT(Heat Deflection Temperature)	ASTM D648	unannealed1.82MPa	°C	56
		unannealed0.455MPa	°C	87
Polymer property				
Melt flow index	ASTM D1238	230°C , 2.16kg	g/10min	12
Density	ASTMD792	23°C	g/cm3	0.935
Filler content	ASTM D5630-94	800°C	%	5.6
Mold shrinkage	ASTM D955	100*100*3.2 mm	%	1.3~1.5

1-The above data are typical values and they are not quality guaranteed values.this data sheet is based on our current knowledge and experience.

1-The above data are typical values.they are only for material selection purpose,and variation within normal telorances are for various colors.

typical values are not our specification and not be used for part or tool design.

2-all propertes ,except Melt Flow Index are measured on injection molded specimens and after 48 hour storage at 23°C and in RH of 50%..

**Scratch test on the ungrained and Black color surface with 3.2mm thickness.

www.kbgco.ir



Kimia Baspar Golpa

PPHR1085

HIPP+ RUBBER+MF

Processing guid (Injection molding condition)

Processing parameters	unit	value
Drying Temperature	°C	50~60
Drying Time	hrs	2~3
Moisture content	%	<0.1
Melt Temperature	°C	200~220
Cylinder Temperature	Rear	°C 200~210
	Middle	°C 200~220
	Front	°C 210~230
Nozzle Temperature	°C	210~230
Mold Temperature	°C	25~50
Back Pressure	kg/cm ²	150~500
Screw Speed	rpm	30~60

Note): Some modifications may be required depending on the specific molding equipment and part configuration.

www.kbgco.ir